

FISA TEHNICA

PLACI DE ASCHII DE LEMN PENTRU AMENAJARI INTERIOARE,
UTILIZATE IN MEDIU USCAT (Tip P1, EKO)



PAL BRUT

Numar Standard	Titlu	Data emiterii
SR EN 309	Placi de aschii de lemn. Definitie si clasificare	Iulie 2006
SR EN 312	Placi de aschii de lemn. Cerinte	Iulie 2011

Specificatii tehnice	Metode testare	Unitate masura	Cerinte				
			SR EN 312:2011				
			Domeniu de grosime (nominala, in mm)				
			>6 pana la 13	>13 pana la 20	>20 pana la 25	>25 pana la 32	>32 pana la 40
Grosime in raport cu dimensiunile nominale	EN 324-1	mm	± 0.3				
Lungime si latime (dimensiuni comerciale)	EN 324-1	mm	± 5				
Toleranta la rectitudinea muchiiilor	EN 324-2	mm/m	≤ 1.5				
Continut de umiditate	EN 322	%	5 - 13				
Toleranta a masei volumice medii in cadrul unei placi	EN 323	%	± 10				
Rezistenta la incovoiere	EN 310	N/mm ²	10.5	10	10	8.5	7
Coeziune interna	EN 319	N/mm ²	0.28	0.24	0.20	0.17	0.14
Continut de aldehida formica	EN ISO 12460-5	Clasa	E1 ≤8mg/100g placa uscata				